

TRUSEAL

Specification Sheet

DESCRIPTION: Glitsa *TruSeal* is a non-yellowing, acrylic, one component waterborne sealer intended for use over bare wood or Glitsa stains. *TruSeal* provides a smooth, uniform coat under Glitsa waterborne finishes. *TruSeal* is designed to work under all Glitsa Waterborne finishes.

CHARACTERISTICS

Cast:	Milky White
Clarity:	Clear when dry
pH:	7.2 - 7.4
Solids Weight:	32.7%
Viscosity (#2 Zahn):	16 - 17 seconds
Pounds/Gallon:	8.73 lbs./gal.
Flash point:	> 200° F. (>93.3° C)
Leveling:	Excellent
Drying Time:	@ 70° F., 50% Relative Humidity Touch: 1 - 1.5 hours To coat: 3 - 4 hours
Coverage:	400 - 600 sq. ft. per gallon
VOC:	< 275 grams per liter

SURFACE PREPARATION

Floor should be prepared according to NOFMA/NWFA approved methods.

Natural wood floors:

- Sand to 100-120 grit and abrade with a 100-120 grit screen.
- Remove all sanding dust from the floor by thoroughly vacuuming and tack with a Glitsa Tack Mop.
- At this time a first coat of *TruSeal* waterborne sealer can be applied to the wood surface following the directions for proper application and dry times.
- Oily woods should be tested to determine compatibility first.

Stained floors:

- Sand to 100-120 grit and abrade with a 100-120 grit screen.
- Remove all sanding dust from the floor by thoroughly vacuuming and tacking with a dry Glitsa Tack Mop.
- Refer to directions on Glitsa Gold Seal Stains for application procedures and dry times.
- After Glitsa stains are thoroughly dry, a coat of *TruSeal* can be applied to the wood surface, following the directions for proper application and dry times.

APPLICATION

For best results apply *TruSeal* at temperatures between 60° - 70° F. (15.6° - 21.1° C.), and 30%-70% relative humidity during application. Additional ventilation and extended dry times may be needed in high humidity or low temperatures. In arid or high temperature areas, 4-6 oz. of water per gallon can be mixed in to retard drying time if necessary. Make sure to have adequate, indirect ventilation while applying Glitsa *TruSeal*. Glitsa recommends straining all waterborne products that have been stored in partially full containers.

- Gently rock container, taking care not to shake vigorously to avoid creating excess bubbles or foam.
- Let container sit for 5 - 10 minutes to allow any bubbles or foam generated to dissipate before coating.
- For best results, apply Glitsa *TruSeal* by using a lightweight T-bar at a coverage rate of 400 - 600 square feet per gallon. Make sure to use a new, lightly water-dampened applicator. *TruSeal* can also be applied with a 10" pad, nylon brush or a roller.
- Start by pouring a 3"-5" puddle of *TruSeal* with the grain of the wood, from wall to wall. Using the snowplow method, pull *TruSeal* with the grain of the wood, from wall to wall.
- Use a cut-in pad or a T-bar to feather out turns.
- Maintain a 3" - 5" puddle at all times, as this will help to ensure even coverage, and a uniform final appearance.
- When *TruSeal* has dried to the touch, ventilate premises, while maintaining temperatures of 60° - 70° F. (15.6° - 21.1° C.). Optimum air quality is achieved through aggressive ventilation.
- Once dry, abrade with a conditioning pad and (2) 240 grit sanding strips. Do not screen. If sealer is applied over stain, take care not to abrade through to the stain.
- A Glitsa waterborne finish may be applied without intercoat abrasion over Glitsa *TruSeal* after a 2 - 4 hour dry time. Abrading is necessary after 6 hours of dry time.
- For best results, vacuum thoroughly and tack the floor with a clean, water-dampened, Glitsa Tack Mop.
- A first coat of any Glitsa waterborne finish may now be applied. Follow directions on finish label.

NOTE: Apply no more than two coats in a 24-hour period.

STORAGE:	Freeze thaw stable. Store above 32 degrees F. If the product should freeze, allow to thaw completely and stir well before using.
SHelf LIFE:	One year in unopened container.
DISPOSAL:	Dispose of unused contents in accordance with local, state and federal regulations.
CONTENTS:	34590-94-8 dipropylene glycol monomethyl ether and 107-21-1 ethylene glycol.



PLEASE READ MATERIAL SAFETY DATA SHEET
RUDD COMPANY, INC. • SEATTLE, WA 98107 • 1-800-444-7833
VISIT OUR WEB SITE AT WWW.GLITSA.COM